

mastaTEX Concrete Specifications

mastaTEX® Concrete Specifications				
Properties of Geotextile	Test Method	40MPA	80MPA	
Carrier Layer - PP Nonwoven Composite	EN ISO 9864	350 g/m ²	350 g/m ²	
Cover Layer - PP Nonwoven	EN ISO 9864	200 g/m ²	200 g/m ²	
Properties of Concrete				
Chemical Composition	XRF	Sand-cement mix	Sand-cement mix	
Density	Typical	1,42 g/cm ³	1,42 g/cm ³	
Setting Start	PN-EN 196-3	> 90 min	> 90 min	
Properties of mastaTEX (1)				
Tensile Strength MD/CMD	EN ISO 10319	≥ 20,0 / 20,0 kN/m (±10%)	≥ 20,0 / 20,0 kN/m (±10%)	
CBR Puncture Strength	EN ISO 12236	≥ 3,0 kN (±10 %)	≥ 3,0 kN (±10 %)	
Properties of mastaTEX (2)				
Compressive Strength	ASTM C 109-02	40 Mpa	80 Mpa	
Bending Tests Based	PN EN 12467:2016-08 5.4.3	6.0 MPa – Class 1	14.5 MPa	
Water Impermeability	PN EN 12467:2016-08 5.4.5-6	No drop of water	No drop of water	
Durability against Freeze-thaw	PN EN 12467:2016-08 5.5.2	RL ≥ 0,75 Pass	RL ≥ 0,75 Pass	
Durability against Heat-rain	PN EN 12467:2016-08 5.5.3	RL ≥ 0,75 Pass	RL ≥ 0,75 Pass	
Durability against warm water	PN EN 12467:2016-08 5.5.4	RL ≥ 0,75 Pass	RL ≥ 0,75 Pass	
Durability against Soak-dry	PN EN 12467:2016-08 5.5.5	RL ≥ 0,75 Pass	RL ≥ 0,75 Pass	
Reaction to fire	PN EN 12467:2016-08 5.6	B-s1, d0*	B-s1, d0*	
Properties of mastaTEX (1)	mastaTEX Concrete 7	mastaTEX Concrete 9	mastaTEX Concrete 10	mastaTEX Concrete 12
Mass per unit area of concrete EN 14196	7000 g/m ² (±10%)	9000 g/m ² (±10%)	10000 g/m ² (±10%)	12000 g/m ² (±10%)
Mass per unit area of mastaTEX EN 14196	7550 g/m ² (±10%)	9550 g/m ² (±10%)	10550 g/m ² (±10%)	12550 g/m ² (±10%)
Thickness EN ISO 9863-1/-2	7,0 mm (±1mm)	9,0 mm (±1mm)	10,0 mm (±1mm)	12,0 mm (±1mm)
Width x Length	(5,0 x 20) m / (2,5 x 20) m			
Quantity	100 m ² / 50 m ²			

(1) before hydration (2) after hydration *complies with EN 13501-1 *Specifications as per manufacturer

Jaybro Group reserves the right to change its product specification at any time. It is the responsibility of the specifier and purchaser to ensure that product specifications used for design and procurement purposes are current and consistent with the products used in each instance.